

5 **What is claimed is:**

1. A composition comprising:
 - (a) a repellent component;
 - (b) a hydrophilic resin;
 - (c) a soil release component; and
 - 10 (d) a crosslinking component.

2. The composition of claim 1 wherein the repellent component comprises a fluorochemical.

3. The composition of claim 2 wherein the fluorochemical comprises a fluorocarbon, said fluorocarbon being selected from the group consisting of:
fluoroacrylates, urethane derivatives, esters, acrylic amides oligomers and
5 polymers.

4. The composition of claim 3 wherein said fluorocarbon comprises a fluoroacrylate.

5. The composition of claim 4 wherein said fluoroacrylate further comprises an ester.

6. The composition of claim 1 wherein said hydrophilic resin is selected from the group consisting of: (meth)acrylate-containing compounds, methacrylate-containing compounds, polyvinyl alcohols, and polysaccharide derivatives.

5

7. The composition of claim 1 wherein said hydrophilic resin comprises a polyurethane-containing compound.

8. The composition of claim 1 wherein said crosslinking component is selected from the group consisting of: derivatives of melamine formaldehydes, epoxides, derivatives of isocyanates, and anhydrides.

9. The composition of claim 8 wherein said crosslinking component comprises a derivative of isocyanate.

10. The composition of claim 1 wherein the ratio(s) of (a):(b):(c):(d) is within the following range(s):
[about 1-10]:[about 1-10]:[about 1-10]:[about 1-10].

11. A textile containing the composition of claim 1.

12. The composition of claim 1 wherein said crosslinking component is
5 hydrophobic.

13. The composition of claim 1 additionally comprising an additive
component, said additive component being selected from the group of additives
consisting of: durable press resins, catalysts, lubricants, softeners, antimicrobial
5 agents, antistatic agents, flame retardant agents, and light stabilizers.

14. A textile or fabric having applied thereon a treating composition,
said treating composition comprising:

- (a) a repellent component;
- 5 (b) a hydrophilic resin;
- (c) a soil release component; and
- (d) a crosslinking component.

15. A textile having applied thereon a composition, said composition
comprising:

--a textile, and

5 --a composition applied to said textile, said composition comprising

- a repellent component;
- a hydrophilic resin;
- a soil release component; and

a crosslinking component;

10 wherein said textile exhibits according to AATCC test method 130-1981 a stain release value to burned motor oil of at least about 3.0 after at least 5 washes.

16. The textile of claim 15 wherein said textile further exhibits, according to said AATCC test method 130-1981, a stain release value to transmission fluid of at least about 3 after at least 5 washes.

17. The textile of claim 15 wherein said textile exhibits an oil or water repellency rating of at least 1 after at least 5 washes.

5 18. A composition for treating a textile, comprising:
 (a) a fluorocarbon-containing repellent component;
 (b) an acrylate or methacrylate-based hydrophilic resin;
 (c) a fluorocarbon-containing soil release component; and
 (d) a hydrophobic crosslinking component.

19. The composition of claim 18 wherein said crosslinking component is a derivative of isocyanate.

20. The composition of claim 19 wherein said derivative of isocyanate is hydrophobic.

21. A textile having applied thereon the composition of claim 18.

22. A textile having applied thereon a treating composition, comprising:

- (a) a textile substrate;
- (b) a fluorocarbon-containing repellent component;
- (c) an hydrophilic resin;
- (d) a fluorocarbon-containing soil release component; and
- (e) a hydrophobic crosslinking component.